



## DATA SHEET

### 8776 MagTac White PolyPro Matte WR

MagTac White PolyPro Matte Plus WR is designed by 130mic white Polypropylene film one side with 25mic porous coating and the other side with 100-110 mic ferrous coating. Economic magnetic receptive film choice. For indoor use and lamination film is required on after printing. Compatible for Aqueous inkjet printing. Idea for all kinds of MagTac production.

### USEFUL INFORMATION

Parameter	Test Method	Value	
Support Material	DIN 60001	Polypropylene paper	
White Point (Color)	CIE Spectrophotometer	L*a*b* ... 94.8, 2.2, -6.8	
Mag. Force	Standard mag. Sheet	15g/cm <sup>2</sup>	
Surface Material		Porous coating	
Weight	DIN 53352	275g/m <sup>2</sup>	
Caliper	DIN 53370	260um / 10mil	
Finish	DIN 53370	Matte	
Work Temp	ISO 13934-1:1999	-20°C - 70°C	
RF Weldable		Yes	
Shelf Time		12 Months	

### APPLICATION COMPATIBILITY

Parameter	Range	Other Factors
Typical Applications	Exhibition, POP, Retail, Signage, Home/Office décor	
Outdoor Durability	12 Months, but largely dependent on methods of installation, printing, and post-print finishing.	
Print Technology	UV, Latex	
Standard Widths	30", 36", 42", 54", 60" x 100 ft - custom widths x length available by special order	

The information above is derived from internal testing by our company and based on information received from our suppliers. The values shown are for reference only, and are provided without guaranty and do not constitute a warranty, expressed or implied. The purchaser should determine, prior to use, the suitability of this material for his/her specific purpose. Data represents an average and is not intended for use as a specification.

New Concept Supply LLC / 2900 Meacham Blvd / Fort Worth, TX 76137

Last Revision: 20200131